



CHONGQING BORIDA CONSTRUCTION CO.,LTD

ADDRESS:Area B, Shandong Dushi Industrial Park, Geleshan Town, Shapingba District,
Chongqing, China

TEL:0086 15823063319

POLYCARBOXYLATE SUPERPLASTICIZER SPECIFICATION

- LIQUID TYPE

ITEM NO.:BRD-501

COLOR:TRANSPARNT LIQUID;LIGHT YELLOW;

PLS CHECK THE FOLLOWING TECHNICAL DATE SHEETS AS REFERENCE FOR CLIENTS:

PHSYSIC TEST		
ITEM NO.:		BRD-501
PH Value		5-7
Density(g/cm ³)		1.1±0.03
CL(%)		MAX 0.3
Solid Content		50%
TEST METHOD:THE RATE OF BRD-501:WATER IS 1:1 IN 1KG SOLUTION. THE DOSAGE OF BRD-501 IS 1% OF CEMENTIOUS (BINDING) MATERIALS.		
Water reducing rate(%)		Min 30
Slump variation in 1 hour(mm)/Standard:100%		90%±3%
Ratio of Compressive Strength	3days	≥160%
	7days	≥150%
	28days	≥140%

PACKING:200KG &1TON DRUM;25KG & 50KG FLEXITANK OR AS CLIENT'S REQUIRED

CHONGQING BORIDA CONSTRUCTION CO.,LTD

ADDRESS:Area B, Shandong Dushi Industrial Park, Geleshan Town, Shapingba District, Chongqing, China